Installation Guide

Casing Seal Kit - CSK

High shrink sleeve for sealing the ends of casing/carrier pipe transitions

Required Kit Components



Canusa Casing Seal Kits - CSK are shipped in pre-cut sizes with a snap-fit closure and a polypropylene profile support skirting. The adhesive is protected from contamination by an inner release liner.

Storage & Safety Guidelines

2

To ensure maximum performance, store Canusa products in a dry, ventilated area. Keep products sealed in original cartons and avoid exposure to direct sunlight, rain, snow, dust or other adverse environmental elements. Avoid storage at temperatures above 80°C (175°F) or below -20°C (-4°F). Product installation should be done in accordance with local health and safety regulations.


These installation instructions are intended as a guide for standard products. Consult your Canusa representative for specific projects or unique applications.

Equipment List




Propane tank, hose, torch & regulator.
Appropriate tools for surface abrasion.
Knife, roller, rags & approved solvent cleanser.
Temperature measuring device.
Hammer, small flat-head screw driver, needle-nose pliers.
Standard safety equipment; gloves, goggles, hard hat, etc.


Surface Preparation



Using a triangular scraper, clean the edges of the casing pipe to remove any burns and dirt from the sealing area.




Clean all exposed steel and adjacent casing pipe with a solvent cleanser to remove the presence of oil, grease and other surface contaminants.




Using a wire brush or sandpaper (40-60 grade), remove all loose surface rust and dirt from the carrier and casing pipes.

Flame Intensity



Clean all exposed steel and adjacent casing pipe with a solvent cleanser to remove the presence of oil, grease and other surface contaminants.




Adjust the flame according to outside conditions.

a. Use bluish-yellow flame for low wind, higher temps.

b. Use blue flame for high wind, lower temperatures


Always aim the torch perpendicular to the pipe and move in a circumferential direction.

Pre-Heat




Pre-heat the casing and carrier pipes to 50°C (120°F) using an appropriate heating device to remove any surface moisture. Use a temperature measuring device to ensure the correct temperature has been reached.

Profile Support Skirting




Place the profile support skirting on the casing pipe with the fingers pointing towards the carrier pipe. Using the tape provide, attach the profile support skirting to the casing pipe. Wrap the profile support skirting tightly around the pipe.



Finish wrapping the profile support skirting around the casing pipe. Use the supplied tape to firmly attach it to the casing pipe.


Sleeve Preparation



Remove the release liner from the sleeve.

www.farwestcorrosion.com www.ccpco.com


Sleeve Installation




Centre the two middle clips on the edge of the casing pipe and wrap the sleeve around the joint to match the insert holes over the clips.




Insert the clips through the holes, push down the closure area to conform to the joint profile. Insert the flat-head screwdriver into the clips and flatten clips with gentle blows from a hammer (use needle-nose pliers if clips become bent or irregularly shaped).



Using broad strokes, heat the sleeve circumferentially around the pipe starting with the end of the casing pipe.




Continue heating from the centre towards the far end of the casing pipe until sleeve recovery is complete and adhesive has oozed out from the side of the sleeve.



In a similar manner, heat and shrink the sleeve around the carrier pipe until sleeve recovery is complete.

Inspection



Visually inspect the sleeve to ensure:

- it has conformed to the casing profile
- it is not damaged
- adhesive has oozed out from all sides.

Backfilling Guidelines

After shrinking is complete, allow the sleeve to cool to below the intended operating temperature of the pipeline before backfilling. To prevent damage to the sleeve, use selected backfill material, (no sharp stones or large particles) otherwise an extruded polyethylene mesh or other suitable shield should be used.

Product Selection Guide

The product selection chart shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.

	Casing DN Size	CSK Sleeve*	Size Range (mm) supplied/recovered	Layflat Length mm
SUC	63	CSK-90/40-525-BK	90/40	280
mensi	90, 110	CSK-125/50-525-BK	125/50	400
	125, 140	CSK-165/65-525-BK	165/65	520
and D	160, 180	CSK-200/80-525-BK	200/80	640
S	200, 225	CSK-250/100-860-BK	250/100	925
Size	250, 280	CSK-320/130-860-BK	320/130	1010
ple	315, 355	CSK-370/150-860-BK	370/150	1155
ailab	400	CSK-450/180-860-BK	450/180	1400
Αv	450	CSK-500/200-860-BK	500/200	1555

^{* 525} and 860 mm sleeve widths are available.

